

发光塑料母粒

Photoluminescent Plastic Master Batch



万能母料 Masterbatch

型号 Model	辉度(mcd/m ²) Luminance	型号 Model	辉度(mcd/m ²) Luminance
ABS7-20	≥160	U-0-1	≥300
ABS7C-10	≥95	U7-50	≥400
ABS6-10 (T)	≥90	U-0-2	≥250
PP-O-1	≥225	USP-2-30	≥200

专用母料 Specification

型号 Model No.	辉度(mcd/m ²) Luminance	型号 Model No.	辉度(mcd/m ²) Luminance
ABS-0-2	≥125	PE-O-1	≥225
ABS-O-3	≥80	PE-O-2	≥125
ABS8-20	≥220	PE-O-3	≥80
PP-O-2	≥125	PC6-20	≥150
PP-O-3	≥80	PC6-30	≥170
PP8-50	≥310	PC6-50	≥180
PP7D-50	≥260	PC7-30	≥200
PP7F-50	≥260		

开关专用料 Special master batch for production of switches

型号 Model No.	辉度(mcd/m ²) Luminance	型号 Model No.	辉度(mcd/m ²) Luminance
ABSLMDY2C-15 (H)	≥125	ABS6-20(GR)	≥35
ABSLMDY2C-15	≥125	ABSLM-15	≥125
ABS9-10 (B)	≥100	ABSSP-4-20(B)	≥35
ABS6-12(GK)	≥90	ABS7-12(GR)	≥28
ABS7-8(B)	≥75	ABS6-12(G)	≥50
ABS7-12(GR)	≥35		

注: U-0-1、U-0-2、PE-0-1、PP-0-1在检验前消光24小时,其余塑料粒检验前消光2小时。



Remarks: Keep in the dark 24 hours before testing for item U-0-1, U-0-2, PE-0-1, PP-0-1, Others in the dark 2 hours before testing.

应用领域/Application field

电器产品: 开关、电话、手工机、视窗、把手、商标、标识、键盘、鼠标等

塑胶制品: 如工艺品、饰品玩具、杯、盘、碟、拉链等日用品。

The master batch is used for production of switches, telephone, display, handles, labels, keyboards, plastic articles, decoration accessories, etc.



大连路明发光科技股份有限公司
DALIAN LUMINGLIGHT CO., LTD.